

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

WHAT IS CLAIMED IS

1. A high-strength carburized part comprising:

a core having a chemical composition of

C: 0.15 to 0.30% by weight,

Si: 0.25 to 1.10% by weight,

Mn: 0.3 to 1.20% by weight,

Cr: 1.25 to 2.0% by weight and

a balance including unavoidable impurities and Fe;

a vacuum-carburized surface having a carbon ratio ranging from 1.0 to 1.5%;

a region extending from the surface to a depth of 50 μm and having a grain boundary oxide layer with a depth of 1 μm or less, wherein a area ratio of carbides of said surface is from 5 to 15% and at least 90% of carbides have a grain size of 5 μm or less , and

wherein the core comprises an interior region which cannot be carburized.

2. The high-strength carburized part as set forth in Claim 1, wherein the core further comprises B and Ti in an amount of from 0.0005 to 0.0050% by weight and from 0.02 to 0.06% by weight, respectively.

3. The high-strength carburized part as set forth in Claim 1, wherein the core further comprises Nb in an amount of from

0.02 to 0.12% by weight.

4. The high-strength carburized part as set forth in Claim 2, wherein the core further comprises Nb in an amount of from 0.02 to 0.12% by weight.

5. The high-strength carburized part as set forth in Claim 1, wherein the core further comprises at least one of: Pb ranging from 0.01 to 0.20% by weight, Bi ranging from 0.01 to 0.10% by weight, Ca ranging from 0.0005 to 0.0050% by weight and S ranging from 0.005 to 0.100% by weight.

6. The high-strength carburized part as set forth in Claim 2, wherein the core further comprises at least one of: Pb ranging from 0.01 to 0.20% by weight, Bi ranging from 0.01 to 0.10% by weight, Ca ranging from 0.0005 to 0.0050% by weight and S ranging from 0.005 to 0.100% by weight.

7. The high-strength carburized part as set forth in Claim 3, wherein the core further comprises at least one of: Pb ranging from 0.01 to 0.20% by weight, Bi ranging from 0.01 to 0.10% by weight, Ca ranging from 0.0005 to 0.0050% by weight and S ranging from 0.005 to 0.100% by weight.

8. The high-strength carburized part as set forth in Claim

4, wherein the core further comprises at least one of: Pb ranging from 0.01 to 0.20% by weight, Bi ranging from 0.01 to 0.10% by weight, Ca ranging from 0.0005 to 0.0050% by weight and S ranging from 0.005 to 0.100% by weight.

9. The high-strength carburized part as set forth in Claim 1, wherein the chemical composition of Si is 0.60% by weight or less.

10. The high-strength carburized part as set forth in Claim 1, wherein the chemical composition of Mn is 0.60% by weight or less.

11. The high-strength carburized part as set forth in Claim 1, wherein the core further includes at least one of: Cu in an amount of 0.30% by weight or less, Ni in an amount of 0.30% by weight or less and Mo in an amount of 0.05% by weight or less.

12. The high-strength carburized part as set forth in Claim 1, wherein the core further comprises at least one of the following:

B and Ti in an amount of from 0.0005 to 0.0050% by weight and from 0.02 to 0.06% by weight, respectively; and

Nb in an amount of from 0.02 to 0.12% by weight; and
Pb ranging from 0.01 to 0.20% by weight, Bi ranging from
0.01 to 0.10% by weight, Ca ranging from 0.0005 to 0.0050% by
weight and S ranging from 0.005 to 0.100% by weight, wherein
at least one of the following is true:

the chemical composition of Si is 0.60% by weight
or less,

the chemical composition of Mn is 0.60% by weight or less
or

Cu in an amount of 0.30% by weight or less, Ni in an amount
of 0.30% by weight or less and Mo in an amount of 0.05% by weight
or less.

13. A method of manufacturing a carburized part, comprising
steps of:

working an alloy that includes 0.15 to 0.30% C by weight,
0.25 to 1.10% Si by weight, 0.3 to 1.20% Mn by weight, 1.25
to 2.0% Cr by weight and a remaining balance including
unavoidable impurities and Fe into a shape of the carburized
part;

vacuum-carburizing said alloy such that a C content on
a surface of said alloy is from 1.0 to 1.5%.

14. The method of claim 13, wherein in a region extending
from a surface of the carburized part to a depth of 50 μ m,

an area ratio of carbides is ranging 5 to 15%, and at least 90% of carbides have a grain size of 5 μm or less and a grain boundary oxide layer with a depth of 1 μm or less.

15. The method of claim 13, wherein said alloy further comprises B and Ti in an amount of from 0.0005 to 0.0050% by weight and from 0.02 to 0.06% by weight, respectively.

16. The method of claim 13, wherein said alloy further comprises Nb in an amount of from 0.02 to 0.12% by weight.

17. The method of claim 15, wherein said alloy further comprises Nb in an amount of from 0.02 to 0.12% by weight.

18. The method of claim 13, wherein said alloy further comprises at least one of: Pb ranging from 0.01 to 0.20% by weight, Bi ranging from 0.01 to 0.10% by weight, Ca ranging from 0.0005 to 0.0050% by weight and S ranging from 0.005 to 0.100% by weight.

19. The method of claim 15, wherein said alloy further comprising at least one of:

Pb ranging from 0.01 to 0.20% by weight;

Bi ranging from 0.01 to 0.10% by weight;

Ca ranging from 0.0005 to 0.0050% by weight or

S ranging from 0.005 to 0.100% by weight.

20. The method of claim 16, wherein said alloy further comprising at least one of:

Pb ranging from 0.01 to 0.20% by weight;

Bi ranging from 0.01 to 0.10% by weight;

Ca ranging from 0.0005 to 0.0050% by weight or

S ranging from 0.005 to 0.100% by weight.

21. The method of claim 17, wherein said alloy further comprising at least one of:

Pb ranging from 0.01 to 0.20% by weight;

Bi ranging from 0.01 to 0.10% by weight;

Ca ranging from 0.0005 to 0.0050% by weight or

S ranging from 0.005 to 0.100% by weight.

22. The method of claim 13, wherein said alloy meets at least one of the following conditions: the chemical composition of Si is 0.60% by weight or less; and the chemical composition of Mn is 0.60% by weight or less; Cu is in an amount of 0.30% by weight or less, Ni is in an amount of 0.30% by weight or less and Mo is in an amount of 0.05% by weight or less.

23. A gear for use in a power transmission, said gear being made of a material comprising:

a core having a chemical composition of

C: 0.15 to 0.30% by weight,

Si: 0.25 to 1.10% by weight,

Mn: 0.3 to 1.20% by weight,

Cr: 1.25 to 2.0% by weight and

a balance including unavoidable impurities and Fe;

a vacuum-carburized surface having a carbon ratio ranging from 1.0 to 1.5%;

a region extending from the surface to a depth of 50 μm and having a grain boundary oxide layer with a depth of 1 μm or less, wherein a area ratio of carbides of said surface is from 5 to 15% and at least 90% of carbides have a grain size of 5 μm or less, and

wherein the core comprises an interior region which cannot be carburized.